

### Product description

Arturo EP1250 mortar floor is a 3-component, epoxy-based, solvent-free floor finish with mineral fillers.

### Area of application

It is suitable as a durable, seamless, coloured finish on cement, anhydrite and magnesite bound subfloors and tiled floors. Arturo EP1250 mortar floor is especially suitable as a finish on floors which will be exposed to medium loads and where high requirements are put on resistance to chemicals and hygiene. For example for:

- Industrial production facilities
- Workshops
- Production areas

Also suitable for creating skirting and upstands (wall connections, etc.).

For other surfaces seek specific advice.

### Optical appearance

Mottled

### Product features

- Resistant to impacts, shock and abrasion
- Good resistance to chemicals
- Can be processed manually or by machine using a power trowel (helicopter)
- Colour of component C: Natural

### Test certificates

- Abrasion resistance:  
Polymer Institut no. P 5887-5
- Fire resistance:  
Interface no. 09010065.CSV.

### Product data

Colour	Natural
Packaging	74.25 kg set (A+B+C) Comp. A = 4.50 kg Comp. B = 2.25 kg Comp. C = 67.50 kg consist of 17.50 kg sand mixture in natural/white/black 25 kg sand natural
Layer thickness	5 - 12 mm
Shelf-life/storage	Ca. 12 months if stored under frost-free conditions in the original packaging
Frost resistance of the cured final product	Yes (but avoid large temperature differences over short periods)

### Technical data

Density of the mixed product	1.80 kg/dm <sup>3</sup>
Mixing ratio	6.06 parts by weight comp. A 3.03 parts by weight comp. B 90.91 parts by weight comp. C
Solids content	100%
Consumption	Layer thickness ca. 1.8 kg/m <sup>2</sup> / mm
Pot life	Ca. 30 minutes*
Hardening/curing	<u>Dust-dry</u> After ca. 6 hours* <u>Foot traffic</u> After ca. 16 hours* <u>Further layers/treatments</u> In ca. 16 to max 24 hours* <u>Mechanical loads</u> After 3 days* <u>Exposure to chemicals and water</u> After 7 days*

\*at 20°C, 65% relative humidity

Abrasion resistance	AR 0.5
Flexural strength	Ca. 20 MPa** (N/mm <sup>2</sup> )
Compressive strength	Ca. 45 MPa** (N/mm <sup>2</sup> )
Fire classification	In accordance with DIN 4102: A 2 In accordance with DIN EN 13501-1: A2 fl-s1
Resistance to chemicals	See the Chemical Resistance list

\*\*after 28 days, 23°C

### Subfloor

The subfloor must be firm, able to bear sufficient loads and have adequate grip. It must be free of grease, oil and non-adherent components. It must also be free of any layers or contaminants that could reduce the adhesion. (Compressive strength at least 25 MPa (N/mm<sup>2</sup>), average tensile strength >1.5 MPa (N/mm<sup>2</sup>), smallest single value > 1.0 MPa (N/mm<sup>2</sup>)).

Prior to work, the subfloor must be adequately dry:

- Cement screed subfloors: ≤ 4 CM%
- Anhydrite: ≤ 0.3 CM%
- Magnesite: < 4 CM%
- Concrete class > B35: ≤ 3 CM%
- Concrete class < B35: ≤ 4 CM%

For Sweden and the UK, below 75% r.h.

### Subfloor preparation

Remove non-adherent layers and contaminants by suitable mechanical means (e.g. shot blasting, milling or sanding). Then remove all dust using an industrial vacuum cleaner.

Larger repairs and the filling of gaps, holes and other unevenness must be carried out with Arturo EP1500 repair mortar.

### Standard layer structure

#### Primer:

Prime the surface with Arturo EP6900 construction resin (see the technical information sheet for details about using this product).

Then lightly sand in the fresh layer (max. 1.0 kg/m<sup>2</sup>) with Arturo sand 0.3-0.8 mm. Finally remove any loose sand before undertaking any further work.

Please ask for special advice if you have a tiled floor.

#### Mortar layer:

Apply Arturo EP1250 mortar layer with a layer thickness between 5 and 12 mm (see: Processing instructions).

#### Liquid-impermeable (anti-slip) sealer layer:

A single layer of Arturo EP7950 sealer gives the mortar floor a liquid-tight surface. Thereafter a further layer of Arturo PU7180 sealer or PU7320 sealer can be applied. For an anti-slip surface use Arturo PU7180 sealer or PU7320 sealer with Arturo anti-slip

powder.

#### Safety information:

The safety information on the label of this product must be heeded.

### Processing conditions

Minimum subfloor temperature: + 10°C and + 3°C above the dew point.

Room/processing temperature:

- Min: + 15°C
- Max: + 30°C
- Optimum: + 20°C

(In general, higher temperatures shorten the pot life, whilst lower temperatures prolong the curing).

Maximum relative humidity: 80%

#### Important:

All components must be acclimatized in the working area prior to use for at least 24 hours.

### Processing instructions for Arturo EP1250

Stir component A thoroughly. Add component B and mix for at least 2 minutes with an electrical mixer (speed ca. 300 – 400 rpm). Then add this mixture to component C. Mix this using a pan mixer until homogeneous (at least 3 minutes). Distribute this mixture over the subfloor using a screed box, pin leveller or trowel. If necessary, level the surface of the mortar (sloping or horizontal) using an aluminium straight-edge. Then preferably compress the surface manually using a trowel, or alternatively using a power trowel (helicopter).

### Cleaning tools

Clean tools and equipment immediately after use. Fully hardened material can only be removed by mechanical means.

### Floor cleaning and care

Use neutral or slightly alkaline cleaning and care agents.

For further information see the cleaning and care instructions of Johnson Diversey.

### Data sources

All technical data, measurements, etc. given on this data sheet are based on laboratory tests. Due to circumstances beyond our control, actual data may deviate from the indicated values.

### Disclaimer

The information on this product sheet concerning the processing and application of this product is based on our experience with the product under standard conditions and with correct product storage and use. In practice, differences between equipment, subfloors and working conditions mean that no guarantee for a specific work result nor any liability, arising out of any legal relationship whatsoever, can

be inferred either from the information on this data sheet or from any verbal advice given, unless caused by intent or gross negligence on our part. In this case the user must demonstrate that he has promptly forwarded to us in writing all necessary information for proper and effective evaluation of the circumstances.

Users must test the products to check whether they are suitable for the intended application.

We reserve the right to amend the information on technical data sheets. The intellectual property rights of third parties must be heeded.

The most recent technical data sheet always applies. This can be requested from us or downloaded from [www.arturoflooring.com](http://www.arturoflooring.com).

Our general terms and conditions of sale and delivery also apply.

### Health and safety at work

GISCODE RE 1 – solvent-free. Not flammable.

Comp. A: Contains epoxy resin / Xi: "irritant".

Comp. B: Contains amine hardener / C: "corrosive".

Both components: Risk of irritation and/or chemical burns to the eyes, respiratory organs and skin. Can cause hypersensitivity if contacted with the skin. If contacted with the skin, immediately wash the skin with a lot of water and soap. If contacted with the eyes, immediately flush the eyes with water and consult a doctor. Wear suitable protective gloves and safety glasses. "Harmful to the environment" in the liquid state, hence prevent discharge into drains, surface waters or onto soil.

Heed, amongst other things, the following: The German Ordinance on Hazardous Substances and Technical Regulation 610 / risk statements / safety recommendations on the container label, safety data sheet, product group information and model instructions of the Association of the Construction Industry (BG Bau) for GISCODE RE 1, guidelines of BG Bau "Epoxy resins in the construction industry".

Neutral odour and ecologically and physiologically harmless once completely dry. Hazard class of component C: none

### Disposal

Do not discharge into drains, surface waters or onto soil. Empty, scraped out and leak-free metal containers can be recycled [Interseroh]. Containers containing non-cured residues of product as well as all other non-cured product residues must be disposed of as hazardous waste. Containers containing cured residues of product can be disposed of as building site waste. For this reason, gather together product residues, mix the components, leave to harden and then dispose of as building site waste.

### CE declaration

	
© 13 Unipro bv Bouwstraat 18 NL-7483 PA HAAKSBERGEN	
EN 13813 SR–B2,0–AR0,5–IR4–B(fl)	
Synthetic resin screed	
Fire resistance:	B(fl)-s1
Release of corrosive substances:	SR
Water permeability:	NPD*
Abrasion resistance:	AR 0.5
Tensile strength: ≥	B 2.0
Impact resistance: ≥	IR 4
Sound insulation:	NPD*
Sound absorption:	NPD*
Heat insulation:	NPD*
Resistance to chemicals:	NPD*
*NPD = No Performance Determined	

Arturo EP1250/16-07-22

Unipro operates a quality assurance system which conforms to the NEN EN ISO 9001/14001 standard. This has been certified by TÜV Nederland. Accordingly, all products and services meet the specifications laid down in this system. As individual circumstances and working practices are unknown, Unipro bv accepts no liability for any damage resulting from the use of any of its products. This information sheet nullifies all earlier documentation sheets. ©Unipro bv 2016. All rights reserved. The copying and/or reproduction of this information sheet by any means is not permitted without the written permission of Unipro bv.